

**$^{10}\text{Be}$  IN TERRESTRIAL BAUXITE AND INDUSTRIAL ALUMINUM:  
AN LDEF FALLOUT**

**J.C. Gregory**

The University of Alabama in Huntsville  
Department of Chemistry  
Huntsville, AL 35899-2900  
Phone: 205/895-6028, Fax: 205/895-6061

204-226

12/7

4P

**A. Albrecht and G. Herzog**  
Rutgers University

Department of Chemistry  
New Brunswick, NJ 08901  
Phone: 908/932-3955, Fax: 908/932-5312

**J. Klein and R. Middleton**  
University of Pennsylvania  
Physics Department

Philadelphia, PA 19104-6396  
Phone: 215/898-8832, Fax: 215/898-2010

**B.A. Harmon and T.A. Parnell**  
NASA, Marshall Space Flight Center  
Space Science Laboratory, ES62  
Huntsville, AL 35812

Phone: 205/544-4924, Fax: 205/544-7754

**SUMMARY**

Work has continued on the search for  $^{10}\text{Be}$  on metals other than aluminum flown on LDEF. Much time-consuming extractive chemistry has been performed at Rutgers University on turnings obtained from the ends of two stainless steel trunnions from LDEF and the prepared samples will be run on the University of Pennsylvania accelerator mass spectrometer.

We have continued to investigate our discovery of naturally-occurring  $^{10}\text{Be}$  contamination in bauxite and industrial aluminums from different sources. Measurements of  $^{10}\text{Be}$  in ores from three different sites, and from four different samples of commercial aluminum have been made. Our investigators indicate that the contamination in commercial aluminum metal originates in its principal ore, bauxite. The levels in some bauxite samples were much greater than the maximum possible for *in situ* production by cosmic ray secondaries. Adsorption of atmospheric  $^{10}\text{Be}$  by surface ores exposed to rainfall is a reasonable explanation.

## INTRODUCTION

The discovery of  $^7\text{Be}$  on front surfaces of LDEF (ref. 1) pointed the way towards an investigation of the possibility of finding other radionuclides produced in the atmosphere (ref. 2). At the present time these appear practically limited to  $^{10}\text{Be}$  and  $^{14}\text{C}$ , though  $^{26}\text{Al}$  must certainly be present in very small quantities (from Ar spallation).

$^{10}\text{Be}$  quantification is particularly attractive since its surface and atmospheric chemistry will be virtually identical to that of  $^7\text{Be}$ . The production and sink functions of both nuclides are well known; therefore, if both surface densities were known on the same piece of satellite material, we should obtain a probe of the vertical transport mechanism of the isotopes in the atmosphere. If the process is diffusion-controlled, the different isotope masses should provide clear indication.

The first attempt to obtain this information was foiled by the discovery that much, if not all, commercial aluminum, including that used to make LDEF and A0114 is naturally contaminated with  $^{10}\text{Be}$ . This is not surprising since many bauxite ores are found close to, or on the ground surface, and may be wetted by rainfall which has scrubbed the Be isotopes out of the air.

In this work we describe some measurements of a sampling of several metal samples from different sources (e.g., kitchen foil, shop aluminum and LDEF metal) and of some bauxite ores from different locations. This gave some idea of the variance, but was not a systematic survey.

Table 1 shows the raw data obtained by AMS. The metals showed levels of 40 to  $110 \times 10^6$  ( $\pm 10\%$ ) atoms of  $^{10}\text{Be}$  per g Al.

**Table 1.  $^{10}\text{Be}$  concentrations of aluminous materials.**

Sample	Source	Mass [mg]	MassAl <sup>1</sup> [mg]	$^{10}\text{Be}/^9\text{Be}$ [ $10^{-15}$ ]	$^{10}\text{Be}$ [ $10^6$ atom/g Al]	Normal Be [ $10^{-9}$ g/g Al]
Al AA Sol'n		140.0	140.0	63±4	61±3	159
Al foil		327.3	327.3	102±7	41±3	58
Al plate	LDEF <sup>2</sup>	256.7	256.7	122±8	75±3	
	LDEF 9-7 <sup>3</sup>	219.7	219.7	101±6	63±5	
	Shop	315.2	315.2	223±22	111±11	140
Bauxite	NBS 69A	1371.8	381.3	74±10	22±2	
Bauxite, Ark.	A 21485 <sup>4</sup>	361	141.5	48±4	15±2	
Bauxite, Haiti		497.7	52.2	33000±200	57200±3800	
Blank <sup>5</sup>				6±2		
Blank <sup>6</sup>		2085		5±1		

Notes: 1) Aluminum concentrations in the bauxites from Arkansas and Haiti were determined by DCP analysis to be 39.2% and 10.5%, respectively; NIST bauxite NBS 69A was used as a standard (27.8% Al). 2) Not flown; 3) Flown. 4) Label given by the American Museum of Natural History (New York, NY, USA); 5) Reagent blank; 6) Procedural blank run with stainless steel.

Bauxites, on the other hand, showed values from 20 to 57,000 x 10<sup>6</sup> atoms <sup>10</sup>Be per g of Al in the ores. Aluminum and beryllium oxides are chemically quite similar and typical bauxites contain normal <sup>9</sup>Be at levels of about 10 ppm. During aluminum refining this is reduced by a factor of about 70 times.

Thus, if we take our measured value for typical metal of 5-10 x 10<sup>7</sup> atoms <sup>10</sup>Be /gAl, this would require a level of 5x10<sup>9</sup> atoms <sup>10</sup>Be/g Al in the ore. This compares with measured values in ores of 2x10<sup>7</sup> atoms per g Al in the Arkansas ore and 6 x 10<sup>10</sup> atoms per g Al in the Haitian ore (equivalent to 6 x 10<sup>9</sup> atoms per g of Haitian ore).

Table 2 shows <sup>10</sup>Be densities per gram of soil or ore. The theoretical maximum was estimated from an average U.S. rainfall and assumes the only sink function to be radioactive decay. On this scale the concentration of <sup>10</sup>Be in the Haitian ore seems remarkable, but not impossible.

**Table 2. <sup>10</sup>Be atom densities per gram soil or ore**

Theoretical max (1m)	1 x 10 <sup>10</sup> atoms g <sup>-1</sup>
US Typ. soil (surface)	2 x 10 <sup>8</sup> - 1 x 10 <sup>9</sup>
NBS and Ark ore	1 x 10 <sup>7</sup>
Haitian ore	6 x 10 <sup>9</sup>

#### Implications for AMS:

Analysts may wish to determine both <sup>26</sup>Al and <sup>10</sup>Be in a rock, in which case they may add both Be and Al carriers, but 5 mg of modern Al may contain 5 x 10<sup>5</sup> (<sup>10</sup>Be atoms), providing a significant unwanted <sup>10</sup>Be background (for comparison, 5g quartz from Bandelier Tuff contains 5 x 10<sup>6</sup> atoms of <sup>10</sup>Be).

- need to use selected carriers
- Al cathodes should not be used for AMS sputtering

#### CONCLUSIONS

- Modern commercial Al contains  
<sup>10</sup>Be at the level of 5-10 x 10<sup>7</sup> atoms/g  
and <sup>9</sup>Be at the 50-100 ppb level.
- Bauxite contains ~ 10 ppm 'normal' <sup>9</sup>Be. About 1% of the Be (both isotopes) makes it through the refining process to Al metal.

- $^{10}\text{Be}$  was almost certainly produced from atmospheric sources rather than *in situ*.
- $^{10}\text{Be}$  concentrations in bauxites reveal their exposure histories to rainfall.
- A study of the distribution of  $^{10}\text{Be}$  in an ore body would give more information on Be transport and retention.
- AMS analysts will now take more care with Al carriers used in  $^{26}\text{Al}$  and  $^{10}\text{Be}$  assays.

A more complete description of the accelerator mass spectrometry measurements and of rock dating using  $^{26}\text{Al}$  and  $^{10}\text{Be}$  is given by the authors in ref. 3 and references therein.

#### REFERENCES

1. *Observation of Be-7 on the Surface of LDEF Spacecraft*, Fishman, G.J., Harmon, B.A., Gregory, J.C., Parnell, T.A., Peters, P., Phillips, G.W., King, S.E., August, R.A., Ritter, J.C., Cutchin, J.H., Haskins, P.S., McKisson, J.E., Ely, D.W., Weisenberger, A.G., Piercey, R.B., and Dybler, T.: **Nature**, 349, 1991, pp678-680.
- 2a. *The Interactions of Atmospheric Cosmogenic Radionuclides with Spacecraft Surfaces*, J.C. Gregory, G.J. Fishman, B.A. Harmon, and T.A. Parnell, **The LDEF First Post-Retrieval Symposium**, Orlando, FL; June 1991. NASA Conference Publication 3134, part 1, p. 237-247.
- 2b. *Cosmogenic Radioisotopes on LDEF Surfaces*, J.C. Gregory, A. Albrecht, G. Herzog, J. Klein, R. Middleton, Abstracts of Second LDEF Post-Retrieval Symposium, San Diego, CA, June 1-5, 1992, NASA Conference Publication 10097, page 25; **Proceedings of Second LDEF Post-Retrieval Symposium**, NASA Conference Publication 3194, pages 231-238.
3.  *$^{10}\text{Be}$  in Bauxite and Commercial Aluminum*, R. Middleton, J. Klein, B. Dezfouly-Arjomandy, A. Albrecht, S. Xue, G.F. Herzog, J. Gregory, Accepted for publication by **Nuclear Instruments & Methods**, February 1994.